

D100 – D110 SWING



GROUP

Decorative products

UTILIZATION

In the interior for the decoration of the wall surfaces and other types of supports. Applicable on wood-iron-metallic alloys-plastics after appropriate preparation.

CHARACTERISTICS

Specific Weight: 1.00 ± 0.050 at 25°C.

Viscosity: 6000 cps ± 500" F6 V10 at 25°C

Yield: 12 sqm/l

Aesthetic Effect: metallic sandblasted

Color: silver - gold - folder colors

Dry leftover: 36%

Packaging: liters 2,5 – 1

DRYING (AIR AT 20°C RELATIVE HUMIDITY 60%)

In Superfice: 30-60 minutes

In Depth: 6-8 hours

FEATURES AND RESISTANCE

It's a highly decorative product easy to apply with excellent adhesion and resistance. It allows to obtain quickly an elegant metallic finish to end sandblasted effect, which seamlessly integrates both modern settings and in those classic. Thanks to these characteristics the product can also be used in highly frequented areas such as public establishments. The high breathability allows its use even in environments where a large amount of moisture ((Sd = 0.090, according to DIN EN 1062-2 (DIN EN ISO 7783-2 painting class I high degree of vapor permeability / high flux density))).

PREPARING THE SURFACE

New wall: brush the surface, apply a coat of **Fissativo Acrilico 1000** Cod.4050 diluted max 1:10 of crumbling plaster or closed pore apply **Fissativo Acrilico Consolidante** cod. 4060, max diluted 1: 1.

Plasterboard: remove dust putty, apply a coat of **Fissativo Acrilico 1000** Cod.4050 diluted max 1:10

Painted surfaces: remove dust from the surface and remove loose paint to the substrate. If present old tempera and / or paint chalking prior application of **Fissativo Acrilico Consolidante** Cod. 4060. If present numerous layers of the fixative tempera paint may not be able to consolidate properly, and, consequently, the decorative product might peel off from the surface when dry. Once the surfaces prepared to apply a hand **Decobase** cod. D900. If necessary apply a second hand.

Supports various (iron - plastic - alloys etc.): Apply a coat of **Primer Tech** cod. 8600.

PRODUCT PREPARATION

Dilution: ready to use

APPLICATION

System: The product should be applied with brush spalter short and crossed brush strokes, trying to distribute the product uniformly. After covering about one square meter pass over the surface with the spalter drain, gently to better distribute the aggregates. In the majority of cases a hand is sufficient to cover the support getting a beautiful sandblasted end pearlescent. If necessary, apply a second coat.

Layers: one

Directive 2004/42 CE:

Category: A/I BA ((Decorative effect, Water Base)

limit value VOC from 01.01.2010: 200 g / l; Maximum VOC content: 200 g / l

Notes:

- Apply the product spent at least 4-6 hours after the application of Decobase
- The folder colors are indicative.
- Always use the same batch of product for the execution of work in the same environment.
- The application on the same surface is to be performed by the same operator.
- Containers and work tools must be washed thoroughly immediately after use with water. The application temperature should not fall below + 5 °C. Close the container tightly after use either. The product is sensitive to frost and must be kept in an environment with the proper temperature.

The data and descriptions in this data sheet are the result of our tests, experience and technical knowledge.

*However, since the product is applied to the outside our control, we can not guarantee that the quality of the source.
You should always verify the suitability of the product to each specific instance.
This technical data sheet supersedes all previous editions.*

**G.&P. F.Ili Tassani S.p.A. Via al Santuario di N.S. della Guardia,44 16162 Genova-Bolzaneto
Tel 010.710715 - Fax 010.710254 - C.P. 6081 - www.tassani.it - e-mail: info@tassani.it**