

D1400010
FOLK



GROUP

Decorative products

UTILIZATION

In the interior for the decoration of the wall surfaces.

CHARACTERISTICS

Specific Weight: 1.20 ± 0.050 at 25°C .

Viscosity: 35000 cps $\pm$ 3000" F6 V10 at 25°C

Yield: 8 sqm/l

Aesthetic Effect: metallic with damasked effect

Color: silver - folder colors

Dry leftover: 46%

Packaging: liters 2,5 – 1

DRYING (AIR AT 20°C RELATIVE HUMIDITY 60%)

In Superfice: 30-60 minutes

In Depth: 6-8 hours

FEATURES AND RESISTANCE

It's a highly decorative product with damasked effect, easy to apply with excellent adhesion and resistance. It achieves a refined chromatic effect, gently metallic, which adapts to any type of environment. The product can be colored tinting system allowing you to create an extensive range of tones that meet every need. The high breathability allows its use even in environments where a large amount of moisture ($S_d = 0.095$, according to DIN EN 1062-2 (DIN EN ISO 7783-2 picture Class I high degree of vapor permeability / high density flow)).

PREPARING THE SURFACE

New wall: brush the surface, apply a coat of **Fissativo Acrilico 1000** Cod.4050 diluted max 1:10 of crumbling plaster or closed pore apply **Fissativo Acrilico Consolidante** cod. 4060, max diluted 1: 1.

Plasterboard: remove dust putty, apply a coat of **Fissativo Acrilico 1000** Cod.4050 diluted max 1:10

Painted surfaces: remove dust from the surface and remove loose paint to the substrate. If present old tempera and / or paint chalking prior application of **Fissativo Acrilico Consolidante** Cod. 4060. If present numerous layers of the fixative tempera paint may not be able to consolidate properly, and, consequently, the decorative product might peel off from the surface when dry.

Once the surfaces are prepared apply a hand **Decobase** cod. D900. If necessary apply a second hand.

PRODUCT PREPARATION

Dilution: ready to use

APPLICATION

System: brush 3x10 + trowel and / or plastic spatula with rounded corners, as an alternative to spalter application on rough surfaces. Apply the product using the brush on a small surface, pulling the product well without leaving too thickly. Then finish the surface using the trowel - plastic spatula, pressing it gently with short strokes and crossed to create a better chromatic effect. If it serves pass again over the surface to flatten any remaining ridges. Take care to keep well clean the trowel and / or spatula during application. This technique is not applicable on rough surfaces, in this case use a brush spalter instead of the spatula / trowel plastic, once spread the product with the brush wipe with him spalter drain making short and crossed brush strokes gently.

Layers: one

Directive 2004/42 CE:

Category: A/I BA ((Decorative effect, Water Base)

limit value VOC from 01.01.2010: 200 g / l; Maximum VOC content: 200 g / l

Notes:

- Apply the product spent at least 4-6 hours after the application of Decobase
- The folder colors are indicative.
- Always use the same batch of product for the execution of work in the same environment.
- The application on the same surface is to be performed by the same operator.
- Containers and work tools must be washed thoroughly immediately after use with water. The application temperature should not fall below $+ 5^{\circ}\text{C}$. Close the container tightly after use either. The product is sensitive to frost and must be kept in an environment with the proper temperature.

*The data and descriptions in this data sheet are the result of our tests, experience and technical knowledge.
However, since the product is applied to the outside our control, we can not guarantee that the quality of the source.
You should always verify the suitability of the product to each specific instance.
This technical data sheet supersedes all previous editions.*

**G.&P. F.lli Tassani S.p.A. Via al Santuario di N.S. della Guardia,44 16162 Genova-Bolzaneto
Tel 010.710715 - Fax 010.710254 - C.P. 6081 - www.tassani.it - e-mail: info@tassani.it**