

D1500010
ENKA



GROUP

Decorative products

UTILIZATION

In the interior for the decoration of the wall surfaces and details. Applicable on any building support after appropriate preparation.

CHARACTERISTICS

Specific Weight: 1.20 ± 0.050 at 25°C.

Viscosity: 40000 cps ± 500 " F6 V10 at 25°C

Yield: 15 sqm/l

Aesthetic Effect: matte dappled

Color: folder colors

Dry leftover: 39 %

Packaging: liters 2,5 – 1

DRYING (AIR AT 20°C RELATIVE HUMIDITY 60%)

In Superfice: 30-60 minutes

In Depth: 6-8 hours

FEATURES AND RESISTANCE

It's a highly breathable and decorative siloxane product, easy to apply, with excellent adhesion and resistance. It allows you to easily get a highly elegant matte aesthetic effect and chromatically uneven suitable for all situations. Applicable in highly frequented places such as public establishments. The high breathability allows use in environments with the presence of moisture ((Sd = 0.076 seconds DIN EN ISO 7783-2 painting class I high degree of permeability to the flow of steam / high density). Associated with a excellent water repellency ($W = 0,08 \text{ kg} / \text{m}^2 * \text{h}^{0.5}$ w according to EN 1062-3).

PREPARING THE SURFACE

New wall: brush the surface, apply a coat of **Fissativo Acrilico 1000** Cod.4050 diluted max 1:10 or apply **Fissativo Acrilico Consolidante** cod. 4060, max diluted 1: 1.

Painted surfaces: remove dust from the surface and remove loose paint to the substrate. If present old tempera and / or paint chalking prior application of **Fissativo Acrilico Consolidante** Cod. 4060. If present numerous layers of the fixative tempera paint may not be able to consolidate properly, and, consequently, the decorative product might peel off from the surface when dry.

Once the surfaces are prepared apply a hand **Decobase** cod. D900. If necessary apply a second hand. Given the type of product it is suggested the application with a short pile roller to prevent the formation of orange peel effect. If you need to sand before the application. If you can not achieve sufficient coverage apply a second coat

Supports various (iron - plastic - alloys etc.): Apply a coat of **Primer Tech** cod. 8600.

PRODUCT PREPARATION

Dilution: ready to use

APPLICATION

System: The product should be applied using a plastic spatula 16 centimeters on a small surface with crossed movement, trying to be consistent in the execution of the design during the application. After covering about one square meter go over the surface with a clean spatula to make the product perfectly smooth. After about 2 hours apply the second coat. The product should be used in two contrasting shades following the examples seen on the color chart.

Layers: two

Directive 2004/42 CE:

Category: A/I BA ((Decorative effect, Water Base)

limit value VOC from 01.01.2010: 200 g / l; Maximum VOC content: 200 g / l

Notes:

- Apply the product spent at least 4-6 hours after the application of Decobase
- The folder colors are indicative.
- Always use the same batch of product for the execution of work in the same environment.
- The application on the same surface is to be performed by the same operator.

· Containers and work tools must be washed thoroughly immediately after use with water. The application temperature should not fall below + 5 °C. Close the container tightly after use either. The product is sensitive to frost and must be kept in an environment with the proper temperature.

*The data and descriptions in this data sheet are the result of our tests, experience and technical knowledge.
However, since the product is applied to the outside our control, we can not guarantee that the quality of the source.
You should always verify the suitability of the product to each specific instance.
This technical data sheet supersedes all previous editions.*

**G.&P. F.lli Tassani S.p.A. Via al Santuario di N.S. della Guardia,44 16162 Genova-Bolzaneto
Tel 010.710715 - Fax 010.710254 - C.P. 6081 - www.tassani.it - e-mail: info@tassani.it**