

D1600000
EPIX



GROUP

Decorative products

UTILIZATION

In exterior and interior for decoration of wall surfaces

CHARACTERISTICS

Specific Weight: 1.10 ± 0.050 at 25°C .

Viscosity: 5000 cps ± 500 " F3 V10 at 25°C

Yield: 15 - 18 sqm/l

Aesthetic Effect: veiled

Color: colorless - folder colors

Dry leftover: $18\% \pm 2$

Packaging: liters 2,5 – 1

DRYING (AIR AT 20°C RELATIVE HUMIDITY 60%)

In Superface: 30-60 minutes

In Depth: 6-8 hours

FEATURES AND RESISTANCE

It's a highly decorative product, for exteriors and interiors, easy to apply to highly matt finish. Applied on the wall surfaces allows for refined glazing effect for decorations that fit perfectly to the buildings included in the historical centers, and also in those of modern architecture. The siloxane nature of the product does not change the natural breathability of the media, effectively protecting them from rainwater. The slow drying is of great help in avoiding the unwanted formation of unsightly seams. Applicable on any type of mural painting, also produced siloxane thick and not. Do not apply lime products not matured.

PREPARING THE SURFACE

New external wall: brush the surface, apply a coat of **Fissativo Polivalente1000** Cod.4260, diluted max 40%. On plaster crumbling previously applying a **Fissativo Acrilsilossanico ad acqua** cod. 4120.

Already painted external surfaces: if the pre-existing paintings were chalking and / or highly degraded it is preferable to remove them by blasting and / or stripping. If paint is well bonded with the support brush to eliminate the pollutants. Then apply one or two coats of **Q3 Acrilsilossanico** cod. 2350 or **Pittura Silossanica** cod. 3420.

New interior wall: clean surfaces, apply a coat of **Fissativo Acrilico Consolidante** Cod. 4060 average diluted 1: 1 and / or **Fissativo Polivalente**, Cod.4260, diluted max 40%. Apply one or two coats of **Decobase** cod. D900.

Already painted interior surfaces: Check the painting cohesion on the media. If the existing paint was powdering apply a **Fissativo Acrilico Consolidante** Cod. 4060. If necessary, repeat the application. Once the surfaces are prepared apply a hand **Decobase** cod. D900. If necessary apply a second hand.

PRODUCT PREPARATION

Dilution: ready to use

APPLICATION

System: The product can be applied with different types of tools, brush, glove for decorative, little trowel, sponge, rag, sea sponge, depending on the type of effect desired. If it is necessary to You can apply a second coat to correct for any application errors, even if it will become the final hue slightly darker. Always work wet on wet to avoid unsightly color overlays.

Layers: one

Directive 2004/42 CE:

Category: A/I BA ((Decorative effect, Water Base)

limit value VOC from 01.01.2010: 200 g / l; Maximum VOC content: 200 g / l

Notes:

- Apply the product spent at least 4-6 hours after the application of Decobase
- The folder colors are indicative and depend strongly on the tool type used and the roughness of the support. It is advisable to carry out an application test before proceeding to execute the work.
- Always use the same batch of product for the execution of work in the same environment.
- The application on the same surface is to be performed by the same operator.
- Containers and work tools must be washed thoroughly immediately after use with water. The application temperature should not fall below $+ 5^{\circ}\text{C}$. Close the container tightly after use either. The product is sensitive to frost and must be kept in an environment with the proper temperature.

*The data and descriptions in this data sheet are the result of our tests, experience and technical knowledge.
However, since the product is applied to the outside our control, we can not guarantee that the quality of the source.
You should always verify the suitability of the product to each specific instance.
This technical data sheet supersedes all previous editions.*

**G.&P. F.Ili Tassani S.p.A. Via al Santuario di N.S. della Guardia,44 16162 Genova-Bolzaneto
Tel 010.710715 - Fax 010.710254 - C.P. 6081 - www.tassani.it - e-mail: info@tassani.it**