

D170998
FUNKY



GROUP

Decorative products

UTILIZATION

In the interior for the decoration of the wall surfaces.

CHARACTERISTICS

Specific Weight: 1.32 ± 0.050 at 25°C .

Viscosity: 20000 cps $\pm$ 2000" F6 V10 at 25°C

Yield: 8 sqm/l

Aesthetic Effect: sandblasted with glazing effect

Color: white - folder colors

Dry leftover: 46%

Packaging: liters 2,5 – 1

DRYING (AIR AT 20°C RELATIVE HUMIDITY 60%)

In Superfice: 30-60 minutes

In Depth: 6-8 hours

FEATURES AND RESISTANCE

It's a highly decorative product, for indoor and outdoor, easy to apply with excellent adhesion and resistance. It allows to obtain quickly an elegant sandblasted finish, chromatically uneven, which fits perfectly in the context of buildings inserted inside the town centers but also in those of modern architecture. The special finish effectively masks small defects often present on plaster. The siloxane matrix of the product does not change the natural breathability of the supports (($S_d = 0.067$, according to DIN EN 1062-2 (DIN EN ISO 7783-2 painting class I high degree of permeability to the flow of steam / high density)). The excellent water repellency effectively prevents the entry of water inside of the plaster ($w = 0.05 \text{ kg} / \text{m}^2 \cdot \text{h}^{0.5}$)).

PREPARING THE SURFACE

New external wall: brush the surface, apply a coat of **Fissativo Polivalente** Cod.4260, diluted max 40%. On plaster crumbling previously applying a **Fissativo Acrilossilossanico ad Acqua** cod. 4120.

Already exterior painted surfaces: if the pre-existing paintings were chalking and / or highly degraded it is preferable to remove them by blasting and / or stripping. If paint is well bonded to the substrate apply a coat of **Fissativo Polivalente** Cod.4260. If they are applied fairly dark colors it is advisable to color the multipurpose fixative in a color similar to that of the finish, or applied quite dark tints

New interior wall: clean surfaces, apply a coat of **Fissativo Acrilico Consolidante** Cod. 4060 average diluted 1: 1 and / or **Fissativo Acrilico 1000** Cod.4050, diluted max 1: 10.

Interior surfaces already painted: check the painting cohesion on the media. If the pre-existing painting appeared powdering apply a **Fissativo Acrilico Consolidante** Cod. 4060. Once the surfaces prepared to apply a **Decobase** cod.D900 hand.

PRODUCT PREPARATION

Dilution: ready to use

APPLICATION

System: The product can be applied with brush spalter (small surfaces) both with a brush (large areas), making short and crossed brush strokes, trying to evenly distribute the aggregate. After covering about one square meter go over the surface with the discharge brush, to better distribute the aggregates.

Layers: one

Directive 2004/42 CE:

Category: AII BA ((Decorative effect, Water Base)

limit value VOC from 01.01.2010: 200 g / l; Maximum VOC content: 200 g / l

Notes:

- Apply the product spent at least 4-6 hours after the application of **Decobase**: in the case of use of **Fissativo Polivalente** Cod.4260 wait 6-8 hours.
- The folder colors are indicative.
- Always use the same batch of product for the execution of work in the same environment.
- The application on the same surface is to be performed by the same operator.
- Containers and work tools must be washed thoroughly immediately after use with water. The application temperature should not fall below $+ 5^{\circ}\text{C}$. Close the container tightly after use. The product is sensitive to frost and must be kept in an environment with the proper temperature.

*The data and descriptions in this data sheet are the result of our tests, experience and technical knowledge.
However, since the product is applied to the outside our control, we can not guarantee that the quality of the source.
You should always verify the suitability of the product to each specific instance.
This technical data sheet supersedes all previous editions.*

**G.&P. F.lli Tassani S.p.A. Via al Santuario di N.S. della Guardia,44 16162 Genova-Bolzaneto
Tel 010.710715 - Fax 010.710254 - C.P. 6081 - www.tassani.it - e-mail: info@tassani.it**