

D180998
SKA



GROUP

Decorative products

UTILIZATION

In the interior for the decoration of the wall surfaces and details. Applicable on any building support after appropriate preparation.

CHARACTERISTICS

Specific Weight: 1.450 ± 0.050 at 25°C.

Viscosity: 14000 cps ± 500" F6 V10 at 25°C

Yield: 10 sqm/l

Aesthetic Effect: matt with metallic luster

Color: folder colors

Dry leftover: 39 %

Packaging: liters 2,5 – 1

DRYING (AIR AT 20°C RELATIVE HUMIDITY 60%)

In Surface: 30-60 minutes

In Depth: 6-8 hours

FEATURES AND RESISTANCE

It's a highly decorative product with excellent adhesion and resistance. It allows you to easily get an elegant bright aesthetic effect generated by the presence of highly selected and reflective glitter. The good breathability allows use in environments with the presence of moisture ((Sd = 0.135 seconds DIN EN ISO 7783-2 painting class I high degree of permeability to the flow of steam / high density - associated with an excellent water repellency ($w = 0.04 \text{ kg} / \text{m}^2 * \text{h}^{0.5}$ according to EN 1062-3).

PREPARING THE SURFACE

New wall: brush the surface, apply a coat of **Fissativo Acrilico 1000** Cod.4050 diluted max 1:10 or apply **Fissativo Acrilico Consolidante** cod. 4060, max diluted 1: 1.

Painted surfaces: remove dust from the surface and remove loose paint to the substrate. If present old tempera and / or paint chalking prior application of **Fissativo Acrilico Consolidante** Cod. 4060. If present numerous layers of the fixative tempera paint may not be able to consolidate properly, and, consequently, the decorative product might peel off from the surface when dry.

Once the surfaces are prepared apply a hand **Decobase** cod. D900. If you need to sand before the application. If you can not achieve sufficient coverage, apply a second man.

Supports various (iron - plastic - alloys etc.): Apply a coat of **Primer Tech** cod. 8600.

PRODUCT PREPARATION

Glitter additive: add the base dose of glitter ready-made, mix the product. You can add more doses if you want to intensify the effect of brightness.

Dilution: ready to use

APPLICATION

System: The product should be applied with a short hair roller (not smooth), crossing the roller and carefully distributing it on the surface, ending the application always in the same direction. He spent at least three hours before applying the second coat.

Directive 2004/42 CE:

Category: A/I BA ((Decorative effect, Water Base)

limit value VOC from 01.01.2010: 200 g / l; Maximum VOC content: 200 g / l

Notes:

- Apply the product spent at least 4-6 hours after the application of Decobase
- After entering the glitter it is best to use the product within 3-4 days.
- The folder colors are indicative.
- Always use the same batch of product for the execution of work in the same environment.

- The application on the same surface is to be performed by the same operator.
- Containers and work tools must be washed thoroughly immediately after use with water. The application temperature should not fall below + 5 °C. Close the container tightly after use either. The product is sensitive to frost and must be kept in an environment with the proper temperature.

*The data and descriptions in this data sheet are the result of our tests, experience and technical knowledge.
However, since the product is applied to the outside our control, we can not guarantee that the quality of the source.
You should always verify the suitability of the product to each specific instance.
This technical data sheet supersedes all previous editions.*

**G.&P. F.lli Tassani S.p.A. Via al Santuario di N.S. della Guardia,44 16162 Genova-Bolzaneto
Tel 010.710715 - Fax 010.710254 - C.P. 6081 - www.tassani.it - e-mail: info@tassani.it**