

D200 LOUNGE



GROUP

Decorative product

UTILIZATION

In the interior for the decoration of the wall surfaces and details. Applicable on any building support after appropriate preparation. Moreover, thanks to its characteristics, it can also be used in highly frequented places such as public environments.

CHARACTERISTICS

Specific Weight: 1.400 ± 0.050 at 25°C .

Viscosity: 7000 cps ± 500 " F3 V10 at 25°C

Yield: 12 sqm/l

Aesthetic Effect: delicately pearly and brilliant effect

Color: white - folder colors

Dry leftover: 33,7% ± 2

Packaging: liters 2,5 – 1

DRYING (AIR AT 20°C RELATIVE HUMIDITY 60%)

In Superfice: 30-60 minutes

In Depth: 6-8 hours

FEATURES AND RESISTANCE

Water-based finish with decorative effect, easy to apply, with excellent adhesion and resistance that reflects any form of light. It allows to obtain an elegant finish with a delicately pearly and brilliant effect, chromatically uneven that integrates perfectly in both modern and classic settings. High washability and resistance to scratches and wear.

PREPARING THE SURFACE

New wall: brush the surface, apply a coat of Fissativo 1000 Cod. 4050 diluted max 1:10 or Fissativo Acrilico Consolidante diluted max 1: 1.

Already painted surfaces: brush the surface and remove old paints that do not adhere to the substrate. If there are old tempera and/or chalking paints, it is advisable to apply a preliminary application of Fissativo Acrilico Consolidante Cod. 4060. If there are numerous layers of tempera paint, the fixative may not be able to properly consolidate them, and consequently the decorative product applied. could browse.

Different substrates (iron - plastics - alloys etc.): apply a coat of Primer Tech cod. 8600 Once the surfaces have been prepared, apply Decobase cod. D900 suitably diluted in one or two coats, Overcoating: 4-6 hours depending on the ambient temperature.

PRODUCT PREPARATION

Dilution: ready to use

APPLICATION

Apply Lounge in its white base or previously colored according to the colors chosen on the chart.

Brushed effect: apply Lounge (diluted maximum 5% with water) with a brush or spalter, proceed with crossed brush strokes distributing the product evenly over the entire surface, avoiding clear squares. After drying (6-8 hours) apply a second coat of product to obtain a more compact effect and with less evident brushstrokes.

Textured effect: apply one coat of Lounge (diluted max 5% with water) with a brush or spalter evenly over the entire surface horizontally. After drying (6-8 hours) apply a second coat of product vertically.

Striped effect: apply one coat of Lounge (diluted max 5% with water) with a brush or spalter evenly over the entire surface in a vertical direction. After drying (6-8 hours) apply a second coat of product always vertically.

Roller application: apply Lounge (diluted maximum 5% with water) with a short-haired roller (not shaved), crossing the rolls and distributing it evenly over the entire surface, finishing the application always following the same direction. After drying (6-8 hours) apply a second coat of product.

Directive 2004/42 CE:

Category: A/I BA ((Decorative effect, Water Base)

limit value VOC from 01.01.2010: 200 g / l; Maximum VOC content: 200 g / l

Notes:

- Apply the product spent at least 4-6 hours after the application of Decobase
- The folder colors are indicative.
- Always use the same batch of product for the execution of work in the same environment.
- The application on the same surface is to be performed by the same operator.

· Containers and work tools must be washed thoroughly immediately after use with water. The application temperature should not fall below + 5 ° C. Close the container tightly after use either. The product is sensitive to frost and must be kept in an environment with the proper temperature.

*The data and descriptions in this data sheet are the result of our tests, experience and technical knowledge.
However, since the product is applied to the outside our control, we can not guarantee that the quality of the source.
You should always verify the suitability of the product to each specific instance.
This technical data sheet supersedes all previous editions.*

**G.&P. F.Ili Tassani S.p.A. Via al Santuario di N.S. della Guardia,44 16162 Genova-Bolzaneto
Tel 010.710715 - Fax 010.710254 - C.P. 6081 - www.tassani.it - e-mail: info@tassani.it**