



TECHNICAL DATA SHEET

D802-SETA

Special breathable plaster with a final alcantara fabric effect

DESCRIPTION

SETA is a special breathable plaster which reproduce a final alcantara fabric effect.

SETA is available in the following bases: SILVER and GOLD.

The ease of application combined with the delicate and refined alcantara effect make this plaster ideal to give a warm touch to both classic and modern environments.

APPLICATION

- The surface to be treated must be dry. Conditions and thickness of the plaster layer affect the drying and hardening time, so make sure it has at least 28 days of curing time, depending on temperature.
- The substrate has to be well prepared and suitable for coating: dry plaster, not any granules from plaster. In case of old walls make sure there is no poor or dusty paint: remove them if necessary as well as flaking paint.
- Apply 1 coat of PRIMER insulation if necessary.
- Apply with a brush or roller, one or two coats of FONDO which has to be thinned up to 5-10 % with water. Allow to dry perfectly, depending on the temperature (from 6 to 12 hours).

APPLICATIONE A SPATOLA:

- After checking the color chart, add to the base, the quantity of dye necessary to obtain the desired colour.
- Sand as necessary using medium or fine grain sandpaper in order to refine any imperfections.
- Proceed shaving the surface with the coloured plaster SETA, using a stainless steel trowel.
- Allow to dry totally and perfectly (from 6 to 12 hours), then refine any imperfections with glass paper.
- Apply the 2nd coat of SETA following the same procedure.
- Clean the trowel with a sponge smoothing the product just applied on the surface.
- Remove the joint material from the trowel with a clean sponge.
- Repeat this operation in order to recreate light and shadow effects, typical of the alcantara fabric.
- Allow to dry to appreciate the effect.

APPLICATIONE A RULLO:

- After checking the color chart, add to the base, the quantity of dye necessary to obtain the desired colour.
- Dilute the product with 5-10% of water.
- Mix carefully until the base is uniformly colored.
- Apply the colored plaster SETA with a short hair roller over the entire surface.
- After 10-15 minutes, smooth the surface with a SPATOLA
- Allow to dry to appreciate the effect (from 6 to 12 hours).

TECHNICAL DATA

Nature of the bond	Mineral acrylic plaster and special resins in aqueous solution
Drying Time	2 h at touch, 6-12 h complete.
Thinning	Ready to use
Yield	3-4m ² /Lt for Trowel;6-7m ² /Lt for Roller
Specific weight	1,166Kg/Lt
Colors	Silver and Gold
Wet aspect	Liquid mellow
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 Years (in sealed, unopened original packing)
VOC	30 gr/l
TVOC	490 gr/l
PH	6-7°C
Cleaning	Water and Soap
Packing	0.750LT,2.5LT

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.